



TOPWAY INDUSTRIES MATERIAL CO.,LTD

Micro size distribution JIS #240~#10000								
	Settlement pipe particle analysis method (μm)				Electric-resistivity grain counter method (μm)			
	ds ₀	ds ₃	ds ₅₀	ds ₉₄	ds ₀	ds ₃	ds ₅₀	ds ₉₄
#240	127	90	60±4.0	48	127	103	57±3.0	40
#280	112	79	52±3.0	41	112	87	48±3.0	33
#320	98	71	46±2.5	35	98	74	40±2.5	27
#360	86	64	40±2.0	30	86	68	35±2.0	23
#400	75	56	34±2.0	25	75	58	30±2.0	20
#500	65	48	28±2.0	20	63	50	25±2	16
#600	57	43	24.0±1.5	17	52	41	20±1.5	13
#700	50	39	21.0±1.3	14	45	37	17±1.3	11
#800	46	35	18.0±1.0	12	38	31	14±1.0	9
#1000	42	32	15.5±1.0	9.5	32	27	11.5±1.0	7
#1200	39	28	13.0±1.0	7.8	27	23	9.5±0.8	5.5
#1500	36	24	10.5±1.0	6.0	23	20	8.0±0.6	4.5
#2000	33	21	8.5±0.7	4.7	19	17	6.7±0.6	4
#2500	30	18	7.0±0.7	3.6	16	14	5.5±0.5	3
#3000	28	16	5.7±0.5	2.8	13	11	4.0±0.5	2
#4000			4.7±0.4		11	8	3.0±0.4	1.3
#6000					8	5	2.0±0.4	0.8
#8000					6	3.5	1.2±0.3	0.6 (ds ₇₅)
#10000							0.8±0.2	